

آتش پویا سپاهان

ATASH POOYA SEPAHAN

تولید کننده فرآورده های نسوز صنعتی
در ابعاد و اندازه های مختلف



ATASHPOOYA REFRACTORIES CO. APCO - D126

General Properties

| | | |
|---------------------|-------|---|
| Classification | | High duty Fireclay Brick |
| Description | | Excellent thermal and mechanical resistance |
| Raw Material Basis | | Fireclay(TABAS) |
| Bond | | Ceramic |
| Packaging | | Pallet |
| Storage Life(Month) | | No expiration date |

Main Chemical Component

| Al ₂ O ₃ (%) | SiO ₂ (%) | Fe ₂ O ₃ (%) | TiO ₂ (%) |
|------------------------------------|----------------------|------------------------------------|----------------------|
| 34-38 | 54-58 | 2.0-3.0 | 3.0-4.0 |

Physical & Thermal Properties

| | | |
|--|-------|----------|
| Refractory Under Load T05 (°C) | | 1300 |
| Bulk Density (gr/cm ³) | | 2.1-2.25 |
| Cold Crushing Strength (Kg/cm ²) | | 350-550 |